

Diene™

TYPICAL PROPERTIES

RUBBER GRADE:

DIENE	A.O	CIS	TRANS	VINYL	T _g , °C	ML/4	OIL PHR	SPECIFIC GRAVITY
35NF	N.S.	40	50	10	-96	37	0	0.90
40NF	S.S.	40	50	10	-96	40	0	0.90
55NF	N.S.	40	50	10	-96	52	0	0.90
600	N.S.	96	4	0	-109	50	0	0.90
635	N.S.	96	4	0	-109	40	0	0.90
645	N.S.	96	4	0	-109	45	0	0.90
140ND	N.S.	97	3	0	-109	40	0	0.90

PLASTIC GRADE:

DIENE	A.O	CIS	TRANS	VINYL	T _g , °C	ML/4	SOL'N VISC	OIL PHR	SPECIFIC GRAVITY
35AC10	N.S.	40	50	10	-96	38	90	0	0.90
40AC10	N.S.	40	50	10	-96	40	85	0	0.90
55AC10/ 55AC15	N.S.	40	50	10	-96	52	162	0	0.90
70AC10/ 70AC15	N.S.	40	50	10	-96	71	250	0	0.90
320AC	N.S.	40	50	10	-96	67	165	0	0.90