

Duradene®

706

Duradene 706 is a non-oil extended solution polymerized styrene-butadiene copolymer having 23.5% bound styrene and a non-staining antioxidant stabilizer system. It can be used as a replacement for SBR 1502 in most applications.

SPECIFICATIONS

RAW POLYMER:

<u>Properties</u>	<u>Target</u>	<u>Minimum</u>	<u>Maximum</u>
Volatile Matter, %	-	-	0.50
Bound Styrene, %	23.5	22.5	24.5
Viscosity, ML/4/212°F	55.0	50.0	60.0

COMPOUND:

Test Recipe (ASTM D3185-1A MIM)

Rheometer (ASTM D2084)

1° Arc, 320°F

Duradene 706	100.00	tc10 (min)	5.5 ± 2.0
IRB 7	50.00	tc50 (min)	8.5 ± 2.0
Zinc Oxide	3.00	tc90 (min)	11.0 ± 2.5
Stearic Acid	1.00	ML (lbs-in)	15.0 ± 2.0
Sulfur	1.75	MH (lbs-in)	47.0 ± 4.0
TBBS	<u>1.00</u>		
	156.75	MS/4/212°F	70.0 ± 10.0

Dec-2006